

UST-7A

NORTH CAROLINA CATHODIC PROTECTION SYSTEM EVALUATION FOR GALVANIC (SACRIFICIAL ANODE) SYSTEMS



- This form must be utilized to evaluate underground storage tank (UST) cathodic protection systems in the State of North Carolina.
- A copy of this completed form must be submitted by the owner/operator to the NCDEQ UST Section, at the address listed below, within 30 days of testing.
- Access to the soil directly over the cathodically protected structure that is being evaluated must be provided.
- A site drawing depicting the UST cathodic protection system and all reference electrode placements must be completed.

I. UST OWNER		II. UST FACILITY	
Name:		Name:	Facility ID:
Address:		Address:	
City:	State:	City:	County:

III. REASON SURVEY WAS CONDUCTED (mark only one)

Routine – 3 year Routine – within 6 months of installation Re-survey as soon as the cathodic protection system reaches steady-state polarization design standards after repair/modification (complete Section IX)

IV. CATHODIC PROTECTION TESTER'S EVALUATION (mark only one)

PASS All protected structures at this facility pass the cathodic protection and continuity survey (indicate all criteria applicable by completion of Section VI).

FAIL One or more protected structures at this facility fail the cathodic protection and/or continuity survey (complete Section VII).

INCONCLUSIVE If the remote and the local do not both indicate the same test result on all protected structures (both pass or both fail), inconclusive is indicated and/or if the continuity survey indicates inconclusive or continuous results the survey must be evaluated and/or conducted by a corrosion expert (Section V must be completed by a Corrosion Expert).

Tester Name:		Name of Certifying Organization (e.g., NACE):	
Company Name:		Certification Type (e.g., CP Tester, CP Technician):	
Address:		Certification Number:	
City:	State:	Zip:	Phone:
CP Tester's Signature:		Date Signed:	Date CP Survey Performed:

V. CORROSION EXPERT'S EVALUATION (mark only one)

The survey must be conducted and/or evaluated by a corrosion expert when: a) an inconclusive is indicated for any protected structure since both the local and the remote structure-to-soil potentials do not result in the same outcome; b) repairs to steel piping protected by galvanic systems are conducted; c) supplemental anodes are added to the tanks and/or piping without following an accepted industry code; or d) when required by NCDEQ.

PASS All protected structures at this facility are judged to have adequate cathodic protection and therefore pass the cathodic protection and continuity survey (indicate all criteria applicable by completion of Section VI).

FAIL One or more protected structures at this facility fail or do not pass the cathodic protection and/or continuity survey and it is judged that adequate cathodic protection is not currently being provided to the UST system (indicate what action is necessary by completion of Section VII).

Corrosion Expert's Name:		NACE International Certification Type or Professional Engineer (PE) Specialty:		
Company Name:		NACE International Certification Number or PE Number / State:		
Address:	City:	State:	Zip:	Phone:
Corrosion Expert's Signature:			Date:	

VI. CRITERIA APPLICABLE TO EVALUATION (mark all that apply)

850 mV ON Structure-to-soil potential more negative than -850 mV with respect to a Cu/CuSO₄ reference electrode with the protective current applied (This criterion is applicable to any galvanically protected structure).

850 mV Instant OFF Structure-to-soil potential more negative than -850 mV with respect to a Cu/CuSO₄ reference electrode with protective current temporarily interrupted (This criterion is applicable only to those galvanic systems where the anodes can be disconnected).

100 mV Polarization Structure tested exhibits at least 100 mV of cathodic polarization (This criterion is applicable to galvanic systems where the anodes can be temporarily disconnected).

VII. ACTION REQUIRED AS A RESULT OF THIS EVALUATION (mark only one)

NONE Cathodic protection is adequate. No further action is necessary at this time.

REPAIR & RETEST Cathodic protection is not adequate. Immediately repair and/or modify cathodic protection system so that adequate cathodic protection is provided and then have the system re-tested as soon as the cathodic protection system reaches steady-state polarization design standards.

VIII. DESCRIPTION OF UST SYSTEM

TANK #	PRODUCT STORED (PREMIUM, REGULAR, DIESEL, ETC.)	TANK CAPACITY (GAL)	CONSTRUCTION MATERIAL (TANKS)	CONSTRUCTION MATERIAL (PIPING)	FLEX CONNECTORS PRESENT (Y/N)
1					
2					
3					
4					
5					
6					
7					
8					
9					
10					

IX. DESCRIPTION OF CATHODIC PROTECTION SYSTEM REPAIRS AND/OR MODIFICATIONS

Cathodic protection systems must be evaluated as soon as the cathodic protection system reaches steady-state polarization design standards following any repairs and/or modifications. Complete this section if any repairs or modifications were made to the cathodic protection system in response to a "failed" evaluation. Certain repairs/modifications as determined by NCDEQ are required to be designed and/or evaluated by a corrosion expert (completion of Section V required).

- Supplemental anodes for a sti-P₃[®] tank were added (attach corrosion expert's design or document industry standard used).
- Supplemental anodes for metallic pipe or flex-connectors were added (attach corrosion expert's design or document industry standard used).
- Galvanically protected tanks/piping not electrically isolated (explain repairs/modifications completed in "Remarks/Other" below).

Remarks/Other:

X. UST FACILITY SITE DRAWING

Attach detailed drawing or use the space provided to draw a sketch of the UST and cathodic protection systems. Sufficient detail must be given in order to clearly indicate where the reference electrode was placed for each structure-to-soil potential that is recorded on the survey forms. Any pertinent data must also be included. At a minimum you should indicate the following: All tanks, piping and dispensers; All buildings and streets; All anodes and wires; Location of CP test stations; Each reference electrode placement must be indicated by a code (e.g., 1,2,3... T-1, T-2, P-1, P-2... etc.) corresponding with the appropriate line number in Section XII of this form.

AN EVALUATION OF THE CATHODIC PROTECTION SYSTEM IS NOT COMPLETE WITHOUT AN ACCEPTABLE SITE DRAWING.

